



>>Entry Name: Zirconium tellurides

Molecular Formula: [TeZr]

>>Variant: Zirconium telluride (ZrTe₂), 11Cl

CAS Registry Number: 32321-65-6

Molecular Formula: Te₂Zr

Molecular Weight: 346.424

Accurate Mass: 349.717161

Percentage Composition: Te 73.67%; Zr 26.33%

Source/Synthesis: Synth. from the elements at 600° or 800°

Physical Description: This phase has a wide range of stoichiometry

>>Variant: Zirconium telluride (ZrTe₃), 11Cl

CAS Registry Number: 39294-10-5

Molecular Formula: Te₃Zr

Molecular Weight: 474.024

Accurate Mass: 479.62339

Percentage Composition: Te 80.76%; Zr 19.24%

Source/Synthesis: Synth. by vapour phase transport with I₂ after heating the elements to 600°

>>Variant: Zirconium telluride (ZrTe₅)

Synonym(s): Telluroxo(tetratelluro)zirconium, 11Cl

CAS Registry Number: 75178-26-6

Molecular Formula: Te₅Zr

Molecular Weight: 729.224

Accurate Mass: 739.435848

Percentage Composition: Te 87.49%; Zr 12.51%

Source/Synthesis: Synth. by heating Te and Zr in a sealed silica ampoule at 500° for 7 days

Use/Importance: Cathode in secondary lithium cells

Physical Description: Semi-metal

Melting Point: Mp 828 dec.°

References:

- Nakazawa, Y. *et al.*, *CA*, **89**, 77804k, (*synth, ZrTe₂, ZrTe₃*)
Kirk-Othmer Encycl. Chem. Technol., 2nd edn., Wiley, 1963, **22**, 629, (*rev*)
Brattas, L. *et al.*, *Acta Chem. Scand.*, 1972, **26**, 3441, (*props, ZrTe₃*)
Gleizes, A. *et al.*, *J. Solid State Chem.*, 1972, **5**, 42, (*synth, cryst struct, ZrTe₂*)
Brattas, L. *et al.*, *Acta Chem. Scand.*, 1973, **27**, 1290, (*synth, props, ZrTe₂*)
Furuset, S. *et al.*, *Acta Chem. Scand.*, 1973, **27**, 2367, (*cryst struct, ZrTe₃*)
Furuset, S. *et al.*, *Acta Chem. Scand., Ser. A*, 1975, **29**, 623, (*cryst struct, ZrTe₃*)
Di Salvo, F.J. *et al.*, *Phys. Rev. B*, 1981, **24**, 2935, (*magnetism, electronic props, ZrTe₃*)
Whangbo, M.H. *et al.*, *Phys. Rev. B*, 1982, **26**, 687, (*band struct, ZrTe₃*)
Hangyo, M. *et al.*, *Ferroelectrics*, 1983, **52**, 151, (*Raman, ZrTe₂*)
Japan. Pat., 1983, 58 154 172; *CA*, **100**, 76233g, (*use, ZrTe₃*)
Taguchi, I. *et al.*, *Solid State Commun.*, 1983, **46**, 299, (*Raman, ZrTe₃*)
Okada, S. *et al.*, *J. Electrochem. Soc.*, 1984, **131**, 2732, (*synth, electrode props, ZrTe₃*)
Fjeldvåg, H. *et al.*, *Solid State Commun.*, 1986, **60**, 91, (*synth, powder struct, ZrTe₃*)