



Molecular Formula: C₁₇H₂₀O₂
Molecular Weight: 256.344
Accurate Mass: 256.14633
Percentage Composition: C 79.65%; H 7.86%; O 12.48%
Melting Point: Mp 59-61.5°
Boiling Point: Bp₅ 190°

>>>**Derivative:** Bis(1,1,2,2-tetrafluoroethyl) ether
Synonym(s): 1,1'-(1-Methylethylidene)bis[4-(1,1,2,2-tetrafluoroethoxy)benzene]

CAS Registry Number: 1544-19-0
Molecular Formula: C₁₉H₁₆F₈O₂
Molecular Weight: 428.321
Accurate Mass: 428.102254
Percentage Composition: C 53.28%; H 3.77%; F 35.48%; O 7.47%
Boiling Point: Bp_{0.9} 136°
Refractive Index: n_D²⁵ 1.4640

>>>**Derivative:** Di-Et ether
Synonym(s): 2,2-Bis(4-ethoxyphenyl)propane

CAS Registry Number: 16079-00-8
Molecular Formula: C₁₉H₂₄O₂
Molecular Weight: 284.397
Accurate Mass: 284.17763
Percentage Composition: C 80.24%; H 8.51%; O 11.25%
Melting Point: Mp 49-50°

>>>**Derivative:** Di-2-propenyl ether
Synonym(s): 1,1'-(1-Methylethylidene)bis[4-(2-propenyloxy)benzene]. 2,2-Bis(*p*-allyloxy)phenylpropane

CAS Registry Number: 3739-67-1
Molecular Formula: C₂₁H₂₄O₂
Molecular Weight: 308.419
Accurate Mass: 308.17763
Percentage Composition: C 81.78%; H 7.84%; O 10.38%
Boiling Point: Bp₅ 120-125°
Refractive Index: n_D²⁰ 1.5648

>>>**Derivative:** Bis(oxiramylmethyl) ether
Synonym(s): 2,2'-[(1-Methylethylidene)bis(4,1-phenyleneoxymethylene)]bisoxirane, 9Cl. 2,2-Bis(4-hydroxyphenyl)propane-bis(2,3-epoxypropyl)ether. Bisphenol A diglycidyl ether. BADGE. DGCBA

Molecular Formula: C₂₁H₂₄O₄
Molecular Weight: 340.418
Accurate Mass: 340.16746
Percentage Composition: C 74.09%; H 7.11%; O 18.80%
Source/Synthesis: Potential food contaminant arising from its use in epoxy resin coatings for food containers such as cans and concrete vats or tanks
Use/Importance: Monomer for epoxy resins
Melting Point: Mp 43°

References:

- Aldrich Library of FT-IR Spectra*, 1st edn., 1985, **1**, 1119A; **2**, 316B, (*ir*, *dipropenoyl*)
Aldrich Library of 13C and 1H FT NMR Spectra, 1992, **2**, 322C; 1296C, (*nmr*)
Aldrich Library of FT-IR Spectra: Vapor Phase, 1989, **3**, 1046A, (*ir*)
v. Braun, J., *Annalen*, 1929, **472**, 1, (*synth*)
England, D.C. *et al.*, *J.A.C.S.*, 1960, **82**, 5116, (*bis(tetrafluoroethyl) ether*)
U.K. Pat., 1963, 923 774; *CA*, **58**, 14311f, (*Di-2-propenyl ether*)
Takenaka, J. *et al.*, *Kogyo Kagaku Zasshi*, 1967, **70**, 2081; *CA*, **68**, 18759, (*synth*)
Bilik, I.M. *et al.*, *Zh. Prikl. Khim. (Leningrad)*, 1967, **40**, 636; *CA*, **67**, 6395, (*synth*)
Encyclopaedia of Polymer Science and Engineering, 2nd edn., Wiley-Interscience, New York, 1986, **6**, 322; 1988, **11**, 648, (*rev*, *polymers*)
Biles, J.E. *et al.*, *J. Agric. Food Chem.*, 1995, **45**, 3541-3544, (*detn*)
Hileman, B., *Chem. Eng. News*, March 24, 1997, 37, (*rev*, *tox*)
Losada, P.P. *et al.*, *J. Agric. Food Chem.*, 1997, **45**, 3493-3500, (*diglycidyl ether*, *detn*, *bibl*)
Lewis, R.J., *Sax's Dangerous Properties of Industrial Materials*, 8th edn., Van Nostrand Reinhold, 1992, BLD500