



>>Entry Name: Aluminium potassium sulfate (AlK(SO₄)₂)

ENTRY UNDER REVIEW

Synonym(s): Sulfuric acid, aluminium potassium salt (2:1:1), 8Cl. Anhydrous alum

CAS Registry Number: 10043-67-1

Related CAS Registry Numbers(s): 14635-80-4

Extra CAS Registry Numbers(s): 15007-61-1

KAl(SO₄)₂

Molecular Formula: AlKO₈S₂

Molecular Weight: 258.207

Accurate Mass: 257.848706

Percentage Composition: Al 10.45%; K 15.14%; O 49.57%; S 24.84%

General Statement: Struct. comprises alternate layers of six coordinate Al³⁽⁺⁾ and K⁽⁺⁾ with SO₄²⁽⁻⁾ between

Source/Synthesis: Synth. by dehydration of the alum

Use/Importance: Commercially available. Coagulating agent for rubber; also used in deodorants and waste water treatment

Physical Description: Colourless hexagonal plates (H₂SO₄)

Solubility: Sol. H₂O (7.74 g per 100 cm³ at 30°); insol. EtOH

Other Data: Corresp. NH₄⁽⁺⁾, Rb⁽⁺⁾, Cs⁽⁺⁾ salts also descr. ΔH_f° -2470 kJ mol⁻¹; ΔG_f° -2240 kJ mol⁻¹; S° 205 J K⁻¹ mol⁻¹

Fluka: 60055

>>Derivative: Dodecahydrate

Synonym(s): Potassium alum. **Kalinite**. Hexaaquaaluminium(3+) hexaaquapotassium(1+) bis(sulfate). α -Alum

CAS Registry Number: 7784-24-9

Molecular Formula: AlH₂₄KO₂₀S₂

Molecular Weight: 474.389

Accurate Mass: 473.975486

Percentage Composition: Al 5.69%; H 5.10%; K 8.24%; O 67.45%; S 13.52%

Source/Synthesis: May be synth. from Al₂O₃, H₂SO₄ + K₂SO₄. Mineral

Use/Importance: Mordant. Used in H₂O purif., paper sizing, dressing skins. Commercially available

Physical Description: Colourless cryst. (H₂O)

Melting Point: Mp 105°

Solubility: Sol. H₂O (11 g per 100 cm³ at 20°); insol. EtOH, Me₂CO

Other Data: Dec. on heating (-9H₂O at 64.5°, -12H₂O at 200°)

Aldrich: 23708-6

Fluka: 60060

Sigma: A6435

References:

- Lipson, H., *Proc. R. Soc. London, A*, 1935, **148**, 664; **151**, 347, (*cryst struct, dodecahydrate*)
Klug, H.P. *et al.*, *J.A.C.S.*, 1940, **62**, 1492, (*dodecahydrate, cryst struct*)
Young, F.E., *J.A.C.S.*, 1945, **67**, 257, (*synth, thermodyn props*)
Palmer, W.G., *Experimental Inorganic Chemistry*, CUP, 1959, 216, (*synth, dodecahydrate*)
Burns, G., *Phys. Rev.*, 1961, **123**, 64, (*dodecahydrate, pmr*)
Tret'yakov, Yu.D. *et al.*, *Russ. J. Inorg. Chem. (Engl. Transl.)*, 1961, 859, (*phase diagram*)
Haussühl, S., *Z. Kristallogr.*, 1961, **116**, 371, (*props*)
Franke, W. *et al.*, *Acta Cryst. B*, 1965, **19**, 870, (*anhydrous, cryst struct*)
Cromer, D.T. *et al.*, *Acta Cryst.*, 1967, **22**, 800, (*nd, dodecahydrate*)
Vandorpe, B. *et al.*, *C. R. Hebd. Seances Acad. Sci. Ser. C*, 1968, **266**, 379, (*related compds*)
Manoli, J.-M. *et al.*, *Bull. Soc. Chim. Fr.*, 1970, 98, (*synth, cryst struct*)
Rems, P. *et al.*, *Inorg. Chim. Acta*, 1971, **5**, 33, (*ir*)
Gal, S., *Therm. Anal., Proc. Int. Conf., 3rd, 1971 (1972)*, 1971, **2**, 559; *CA*, 1973, **78**, 131564, (*dodecahydrate, thermal anal*)
Pannetier, G. *et al.*, *Bull. Soc. Chim. Fr.*, 1972, 485, (*analogues*)
Strupler, N. *et al.*, *Bull. Soc. Chim. Fr.*, 1974, 1830, (*dodecahydrate, ir*)
Eysel, H.H. *et al.*, *Z. Anorg. Allg. Chem.*, 1976, **424**, 68, (*Raman*)
Hurlburt, H.Z., *Encycl. Chem. Process. Des.*, 1977, **3**; *CA*, 1978, **88**, 193727, (*rev*)
Kirk-Othmer Encycl. Chem. Technol., 3rd edn., Wiley, 1978, **2**, 250
Couchot, P. *et al.*, *Rev. Chim. Miner.*, 1978, **15**, 373, (*anhydrous, ir, Raman*)
Bhat, S.V. *et al.*, *Curr. Sci.*, 1984, **53**, 27, (*Al-27 nmr, anhydrous*)
Eckert, H. *et al.*, *J.A.C.S.*, 1986, **108**, 2140, (*dodecahydrate, S-33 nmr*)
Encyclopedia of Food and Color Additives, (ed. Burdock, G.A.), CRC Press, 1997, 115-118
Lewis, R.J., *Sax's Dangerous Properties of Industrial Materials, 8th edn., Van Nostrand Reinhold*, 1992, AHF100; AHF200