



>>Entry Name: 11-Aminoundecanoic acid, 9CI

CAS Registry Number: 2432-99-7

Related CAS Registry Numbers(s): 29833-32-7

$\text{H}_2\text{NCH}_2(\text{CH}_2)_9\text{COOH}$

Molecular Formula: $\text{C}_{11}\text{H}_{23}\text{NO}_2$

Molecular Weight: 201.308

Accurate Mass: 201.172879

Percentage Composition: C 65.63%; H 11.52%; N 6.96%; O 15.90%

Use/Importance: Homopolym. gives Nylon-11

Melting Point: Mp 190-192° (185-187°)

Aldrich: A8260-5

Fluka: 9620

Sigma: A4897

>>Derivative: Me ester

CAS Registry Number: 28691-27-2

Molecular Formula: $\text{C}_{12}\text{H}_{25}\text{NO}_2$

Molecular Weight: 215.335

Accurate Mass: 215.188529

Percentage Composition: C 66.93%; H 11.70%; N 6.50%; O 14.86%

Physical Description: Solid (MeOH) (as hydrochloride)

Melting Point: Mp 160° (hydrochloride)

>>Derivative: Et ester

CAS Registry Number: 15351-28-7

Molecular Formula: $\text{C}_{13}\text{H}_{27}\text{NO}_2$

Molecular Weight: 229.362

Accurate Mass: 229.204179

Percentage Composition: C 68.08%; H 11.86%; N 6.11%; O 13.95%

Boiling Point: Bp_{0.1} 125-130°

>>Derivative: Lactam

see 1-Azacyclododecan-2-one, [BHD31-E](#)

References:

Aldrich Library of FT-IR Spectra, 1st edn., 1985, **1**, 579B, (*ir*)

Aldrich Library of NMR Spectra, 2nd edn., 1983, **1**, 491A, (*nmr*)

Garmaise, D.L. *et al.*, *J.A.C.S.*, 1958, **80**, 2332, (*synth*)

Pied, J.P., *Ann. Chim. (Paris)*, 1960, **5**, 469, (*synth*)

Zahn, H. *et al.*, *Chem. Ber.*, 1961, **94**, 2470, (*synth*)

East Ger. Pat., 1963, 25 925; *CA*, **60**, 10553f, (*synth*)

Tosi, L., *Spectrochim. Acta*, 1963, **19**, 1097, (*ir*)

IARC Monog., 1986, **39**, 239; *Suppl.* 7, 57, (*rev, tox*)

Encyclopaedia of Polymer Science and Engineering, Wiley-Interscience, New York, 2nd edn., 1988, **11**, 370, (*rev, polymers*)

Lewis, R.J., *Sax's Dangerous Properties of Industrial Materials*, 8th edn., Van Nostrand Reinhold, 1992, AMW000